

DESCRIPTION

This formula is a high-temperature silicone system developed from a proprietary blend of resins and pigments to provide service up to 1200°F (649°C). This is designed to be a very fine textured metallic coating for steel and aluminum substrates.

Product Benefits

- Enhanced charging and handling characteristics
- Provides excellent texture over a wide range of film thickness
- Good long-term performance at 800°F (427°C) while maintaining color, gloss and film integrity.
- Excellent UV resistance for outdoor use on aluminum or aluminized substrates.
- Designed to be more compatible and to reduce cross contamination with other coatings

SPECIFICATIONS

Cure cycle [Temperature for substrate]	20 mins at 400°F (204°C)
	12 mins at 425°F (218°C)
	8 mins at 450°F (232°C)
Specific Gravity	1.84 +/-0.05
Theoretical coverage for 1 mil	105 ft ² per pound
Film builds between	1.20 and 2.80 mils
Recommended at	2.00 mils

Heavier film builds are not recommended.

TYPICAL PROPERTIES

Adhesion (ASTM D3359)	4B – 5B
Gloss at 60°(ASTM D523)	5 – 15
Impact Resistance (ASTM D2794-90)	60 lb. Direct 20 lb. Reverse
Pencil Hardness (ASTM D3363)	>2H

PERFORMANCE TESTING

Continuous testing for 48 hours at 800°F (427°C) shows this product holds gloss, color and physical integrity at this service temperature. Testing for 168 hours at 1000°F (538°C) indicates good performance up to 24 hours with some gloss change at extended times at elevated temperatures. Testing indicates good film integrity after exposure to temperatures of 1200 °F (649°C).

SURFACE PREPARATION

High temperature coatings require cleaner substrates to maintain a good bond between metal and coating. Abrasive media blast is an excellent method of surface preparation. Chemical pretreatments are effective, but must be rinsed to a clean surface with no dirt or cleaner residue. *Phosphate pretreatments have their own temperature limits that must be observed.* Contact your chemical pretreatment supplier. Also substrates have limits that must be observed.

FINISHED PRODUCT HANDLING

The finished coated product is not as tough as standard powder coatings. Care must be exercised in handling and packing to ensure that finish is not damaged.

PRECAUTIONS

Read and understand the MSDS before using. This product is more temperature sensitive than normal powders and should be used at temperatures below 77°F (25°C). This product is more susceptible to moisture than other powder products. Because of the electrostatic properties of this powder a fluidizing feed hopper with higher air flow must be used.

**We recommend testing for compatibility with other products that you use before purchasing.*

STORAGE

This product should be stored at temperatures below 77°F (25°C) for up to 6 months. Under carefully controlled conditions, shelf life may be extended.

LIMITATIONS

The technical data and suggestions for use in this product data sheet are currently correct to the best of our knowledge, but are subject to change without notice. Because application and conditions vary, and are beyond our control, we are not responsible for results obtained in using this product, even when used as suggested. The user should conduct tests to determine the suitability of the product for the intended use. Our liability for breach of warranty, strict liability in tort, negligence or otherwise is limited exclusively to replacement of the product or refund of its price. Under no circumstance are we liable for incidental and consequential damages.