Technical Data Sheet

1A464E Chimney and Roof Flashing

PRODUCT DESCRIPTION

Stove Bright® Chimney & Roof Flashing High Temp Paint provides hearth installation professionals and homeowners alike with an exterior durable, high temperature paint for finishing exposed pipe above the roof line

Color: Available in a wide variety of colors
Gloss: Low

PHYSICAL PROPERTIES

Property	Result
Volume Solids	7 - 12 % ±2
Coverage at 1 mil (25.4 µm)	15 – 18 ft.² per can 1.4 – 1.67 m² per can
Recoat	Immediately or after 24 hours
Clean-up overspray	Xylene or Toluene
Dry time at 70°F(21°C) and 50% relative humidity	
Dry to touch	15 minutes
Dry hard	2 hours

SURFACE PREPARATION

Surface must be clean, dry and free of oil, grease, mill scale and other contaminants. Possible cleaning methods include solvent scrub, wire brushing, or sanding. 1A464E has excellent durability and UV resistance.

MIXING

Shake can vigorously for at least one minute after mixing ball rattles to ensure uniform spray and prevent clogging. Shake can occasionally during use. Test spray on a scrap to adjust for pattern and distance to prevent dry spray. Position the can 10 to 12 inches from surface to avoid drips and runs. For substrates that are more difficult to adhere to, first apply a light tack coat and allow it to dry for 25 minutes. Then apply the first complete flow coat. Apply with steady even strokes.

FORREST Technical Coatings
1011 McKinley Street
Eugene, OR 97402 USA
www.forrestpaint.com
info@forrestpaint.com
Ph: (800) 537-7201
(541) 342-1821

Technical Data Sheet

1A464E Chimney and Roof Flashing

APPLICATION

Application Parameters

Relative Humidity	30 – 85%
Minimum Temperature	50°F (10°C)
Maximum Temperature	90°F (27°C)

***** Cans will dispense product best when the temp is 65°F - 85°F

When applying with an aerosol, two or three light coats are better than attempting one heavy coat.
Your first coat should be a “mist” coat, it should look like dots on the surface. Trying to cover the surface in a single pass will most likely result in drips and runs of this thin paint. Paint should be sprayed from about 12 to 15 inches from the surfaced. If you get too close, the paint will likely drip or run. If you get too far away, the paint will dry in the air and result in a gritty finish.

STORAGE

The product must be stored in accordance with local and national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 73°F (23 °C) = minimum of 12 months *

*When kept in recommended storage condition and original unopened containers.

DANGER! FLAMMABLE LIQUID AND VAPOR.

Vapors may ignite explosively. Keep away from heat, sparks, or open flame. Use only in well ventilated area. Protect all workers from paint vapors. Wear eye protection.

CAUTION

Adequate health and safety precautions should be observed during storage, handling, use and curing periods.

READ SAFETY DATA SHEETS BEFORE USING THIS PRODUCT

DISCLAIMER

FORREST Technical Coatings
1011 McKinley Street
Eugene, OR 97402 USA
www.forrestpaint.com
info@forrestpaint.com
Ph: (800) 537-7201
(541) 342-1821

Technical Data Sheet

1A464E Chimney and Roof Flashing

The technical data and suggestions for use in this product data sheet are currently correct to the best of our knowledge, but are subject to change without notice. Because application and conditions vary, and are beyond our control, we are not responsible for results obtained in using this product, even when used as suggested. The user should conduct tests to determine the suitability of the product for the intended use under then existing conditions. Our liability for breach of warranty, strict liability in tort, negligence or otherwise is limited exclusively to replacement of the product or refund of its price. Under no circumstances are we liable for incidental or consequential damages.

FORREST Technical Coatings
1011 McKinley Street
Eugene, OR 97402 USA
www.forrestpaint.com
info@forrestpaint.com
Ph: (800) 537-7201
(541) 342-1821