1A29S Aerosols Technical Data Sheet

PRODUCT DESCRIPTION

29S Series is a solvent borne epoxy ester coating, specifically designed for foot traffic on most properly prepared substrates, such as steel, fiberglass, treated aluminum, concrete, and wood.

Colors: Clear, White, Black, Russet Red, Blue, Safety Yellow, Sequoia Green, Brown, and Gray
Sheen: Satin

PRODUCT DATA

Property	Result
Theoretical Coverage	12 – 15 ft²/can
Overspray Clean up	Immediately w/ solvent
Dry Time *	20-30 min @ 77°F

*Wait 24 hours before allowing foot traffic on the coated surface.

SURFACE PREPARATION

Surface must be clean, dry and free of oil, grease, mill scale and other contaminants. Possible cleaning methods include abrasive blasting (preferred) in accordance with SSPC-SP-6, solvent cleaning in accordance with SSPC-SP-1, or hand and power tool cleaning in accordance with SSPC-SP-2 or SP-3. Repaired steel should then be solvent cleaned with Xylene, Toluene, or lacquer thinner. Use clean solvent and clean white wiping rags. Do not use colored rags containing dye, which may dissolve in the solvent leaving incompatible contaminants on the surface.

MIXING

Mix Directions
Shake the can for 2 minutes to completely mix the paint pigments, metallics and solvents for the best possible finish. If you do not shake aerosols long enough, this can lead to spitting or clogging at the tip.

FORREST Technical Coatings
1011 McKinley Street
Eugene, OR 97402 USA
www.forrestpaint.com
info@forrestpaint.com
Ph: (800) 537-7201
(541) 342-1821

APPLICATION

Application Parameters

Relative Humidity	30 – 85%
Minimum Temperature	50°F (10°C)
Maximum Temperature	90°F (27°C)

* Cans will dispense product best when the temp is 65°F - 85°F

** We recommend allowing product to air dry for a minimum of 24 hours, before any foot traffic.

When applying with an aerosol, two or three light coats are better than attempting one heavy coat.
Your first coat should be a “mist” coat, it should look like dots on the surface. Trying to cover the surface in a single pass will most likely result in drips and runs of this thin paint. Paint should be sprayed from about 12 to 15 inches from the surfaced. If you get too close, the paint will likely drip or run. If you get too far away, the paint will dry in the air and result in a gritty finish.

STORAGE

The product must be stored in accordance with local and national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 73°F (23 °C) = minimum of 12 months *

*When kept in recommended storage condition and original unopened containers.

DANGER! FLAMMABLE LIQUID AND VAPOR.

Vapors may ignite explosively. Keep away from heat, sparks, or open flame. Use only in well ventilated area. Protect all workers from paint vapors. Wear eye protection.

CAUTION

Adequate health and safety precautions should be observed during storage, handling, use and curing periods.

READ SAFETY DATA SHEETS BEFORE USING THIS PRODUCT

DISCLAIMER

The technical data and suggestions for use in this product data sheet are currently correct to the best of our knowledge, but are subject to change without notice. Because application and conditions vary, and are beyond our control, we are not responsible for results obtained in using this product, even when used as suggested. The user should conduct tests to determine the suitability of the product for the intended use under then existing conditions. Our liability for breach of warranty, strict liability in tort, negligence or otherwise is limited exclusively to replacement of the product or refund of its price. Under no circumstances are we liable for incidental or consequential damages.

FORREST Technical Coatings
1011 McKinley Street
Eugene, OR 97402 USA
www.forrestpaint.com
info@forrestpaint.com
Ph: (800) 537-7201
(541) 342-1821